



With its innovative formula, GLUKON®premium wmc represents the latest state of development in the field of solvent-based adhesives. Working with GLUKON®premium wmc is less harmful for humans and the environment than using comparable solvent-based adhesives currently on the market. GLUKON® premium wmc offers permanent adhesion to a range of different substrates with an extremely high degree of temperature resistance. GLUKON®premium wmc stands out with its excellent initial bonding and high final strength (>150 PSI). For this reason, this adhesive is particularly well suited to moulded bonding and bonding stainless steel sheets to board materials. The very high solids content ensures excellent bonding with just one coating. GLUKON®premium wmc is used wherever there are the highest demands for final bonding strength and dimensional stability.

- + Fulfils the A+ criterion per the French VOC emissions class ordinance
- + The spray adhesive is emissions tested according to the Agbb scheme
- + Emission tested per Eurofins Indoor air comfort criteria
- + M1 classified per RTS sr.
- + Tested for rail vehicles DIN 45545-2 classified



MATERIALS

GLUKON®premium wmc is suitable for bonding HPL to wooden panels, plywood, multiplex, chipboard, décor chipboard, MDF, bending plywoods, slitted MDF, glass, cork, wood, almost all types of plastic, rubber, wall claddings, carpet, concrete, metals, textiles, foam, painted steel and much more.

FEATURES

- + Adhesive is applied quickly and easily
- + Mobile, ready for immediate use without power or compressor
- + Spraying method: Web spray
- + Flash-off time: approximately 1- 2 minutes depending on ambient temperature/humidity
- + Open time: approx. 4 hours
- + The cured adhesive is not flammable
- + Dichloromethane-free

TECHNICAL DETAILS

- + Description: Solvent-based sprayable contact adhesive
- + Colour: Transparent, white-ish
- + Solid content: approx. 36 %
- + Resistance to temperature: approx. 110°C (brief period)
- + Shear strength: >150 psi
- + Range per 13.6 kg pressure container: approximately 80 - 100 m² (application on both sides)
- + Coverage per 500 ml tin: approx. 3 m² (application on both sides)

INSTRUCTIONS FOR USE

Before every job, it is necessary to check whether the selected adhesive is suited to the requirements profile of the materials used and the intended site of use!

The materials must be conditioned with each other before bonding or have a material moisture/temperature adapted to the final installation location (24/48h). The materials to be bonded must be dry, clean and without dust, grease and cracks. Use only acetone for de-greasing or isopropanol in the case of sensitive surfaces (e.g. plastic or plexiglas). The suitability of the selected cleaner should be checked for compatibility beforehand on a non-visible surface. For optimum bonding, metals and smooth surfaces must be cleaned and degreased with a lint-free cloth. Then roughen the materials by cross-grinding with sandpaper (recommendation: aluminium oxide, 100 grade). After that, degrease the materials once again.

To ensure optimum results, the adhesive should be used at temperatures of 15 - 25°C (ideally 20°C). This also applies to the materials to be bonded.

With first use, connect the hose and gun to the container. Then slowly open the container valve and check the system is leak-tight. The system is now ready for operation.

To apply the adhesive, hold the gun approx. 10 cm (hand width) above the application surface. The rule of thumb for correct application here is: Spray jet width = distance to the workpiece.

Always apply the adhesive evenly, crosswise to both sides to be bonded (surface 1 vertically, surface 2 horizontally). Avoid puddles of adhesive (solvent build-ups). Application quantity approx. 70 - 85g/m²/wet. Double application is recommended around edges or on very absorbent substrates, e.g. block board or plywood. Material joints that will be exposed to moisture or water after bonding, must be protected by the construction or by using a suitable adhesive or sealant (MS polymer or PU adhesive). Allow the adhesive to dry for

approx. 1 - 2 mins. until the solvents have flashed off completely (finger test). Compliance with the flash-off time is extremely important and must be **precisely** observed! The open time is approx. 4 hours. In order to align large format surfaces better, spacers (e.g. dowel rods or spacer strips) can be used on the carrier material. Now the materials can be placed. They must be free of bubbles as it will not be possible to shift the materials afterwards! This is best done by carefully rubbing from the centre outwards. Then press/roll the materials together firmly (contact pressure approx. 2.5 - 3 kg/cm²). **High contact pressure is essential for optimum bonding!** The materials can be further processed immediately. It takes about 24/48 hours until the adhesive is completely cured. Lock the spray gun after use. The valve on the adhesive container must **NEVER** be closed unless the container is being replaced with a new one or it is closed for transport to the construction site. Please use Glukon Citrus Cleaning Spray for removing adhesive residues from surfaces. Before use, please read our Glukon instructions for use (enclosed with the container), which are also available to download from: www.glukon.de

Important information: Solvent-based coatings, such as oils, waxes, NC lacquers, etc., could attack the adhesive and are therefore not suitable for coating with bonded materials! Depending on the raw material base, some cleaning agents may also attack the adhesive and for this reason avoid directly spraying onto the adhesive joints when cleaning soiled surfaces. Recommendation: Do not apply the cleaning agent directly to the workpiece, but rather apply it to a lint-free cloth and clean the surfaces with this. Glukon premium wmc is not suitable for bonding: PE, PP, polystyrene and plasticised materials such as PVC and CV coatings, vinyl and artificial leather!

APPLICATION CHECKLIST

- + Does the selected adhesive match the requirements profile and the intended site of use?
- + Are the materials to be bonded correctly acclimatised (at least 48 hours) or adjusted to the prevailing climatic conditions at the place of installation?
- + Are the materials to be bonded dry, clean and free of dust and grease? Degrease only with acetone or isopropanol. Metals and smooth surfaces should be additionally roughened and then degreased again.
- + Do the application temperatures of the adhesive, the materials and the environment fall inside the permissible parameters (15 - 25 °C)?
- + Are you sufficiently familiar with how to apply the adhesive? Distance between the spray gun and the workpiece, spray jet width and spraying speed? Please visit our website: www.glukon.de/anwendung and watch our application video for further information.
- + Do you know the respective flash-off times and open times for the adhesive to be used? These must be adhered to!
- + Are the materials free of tears or similar damage?
- + Has the work process been thought through? Can dirt be ruled out when applying the adhesive?
- + Is the system ready to use? Is the product well shaken? Pistol and nozzle should spray without problem.
- + Is the correct nozzle being used? Please only use our Glukon standard nozzle with our web spray adhesives.
- + Are all tools (e.g. dowel rods) ready for laying the materials without bubbles?
- + Are pressure rollers ready or is the press available and set to the required pressure (2.5 to 3 kg/cm²)?
- + Is health and safety ensured?

HEALTH & SAFETY / SAFETY INSTRUCTIONS

- Processing must only be performed by competent individuals.
- Personal protective equipment should be worn when working with the GLUKON[®] spray adhesive system. Please also be sure to observe our safety data sheets in this regard!
Good ventilation of the workplace/site must be guaranteed or ensured by means of suitable technical measures (e.g. EX-protected extraction unit or stationary extraction).
Directly breathing in the solvent should be avoided.
- With insufficient ventilation or incorrect use there is a risk of an explosive gas/air mixture forming! This results in a danger to life!
The production of naked flames and excessive heat (+50°C) must be avoided in general!
- The vessel is pressurised and must be protected against damage (e.g. valve being struck off, being dropped, the effects of heat, etc.).
- Never forcibly open full containers or containers that have not been completely emptied! Risk of explosion!

STORING AND HANDLING THE GLUKON[®] CONTAINER

Must be stored at a temperature between +10 °C and +50 °C. The container is under pressure. Protect containers from direct sunlight and heat sources. Do not store on a cold concrete floor. Avoid damage to the container or penetration by foreign objects. The containers may not be refilled! Transport containers in an upright position and secure against shifting/toppling. Close container valve when transporting. Protect containers from rain. Handle containers carefully. Do not throw or drop. Only store in well-ventilated rooms. Containers showing damage from the outside, such as dents or

valve damage, are to be disposed of professionally. Do not stick objects in the spray head! Please also refer to the safety datasheet (Point 7 and Point 14) for our GLUKON[®] containers! GLUKON[®] can be stored under the recommended conditions for at least 18 months.

ATTENTION! SHAKE/ROLL THE CONTAINER WELL FOR AT LEAST 1 MINUTE BEFORE FIRST USE AND IF NOT USED FOR EXTENDED PERIODS. PROTECT FROM FREEZING. ENSURE THE CORRECT TEMPERATURE WHEN WORKING! (min. +15°C).

DISCLAIMER

We always recommend trying the adhesive on your materials first. Please refer to our technical leaflets and the adhesive recommendations of the respective material manufacturer. It is important to test all materials to be bonded before production. The operator using is responsible for checking whether **GLUKON[®] premium wmc** is suitable for the respective application. **Industrial adhesive. Exclusively for commercial applications.**

The above details are based on results in practice and tests undertaken by us. As we have no influence on the choice of materials or the conditions of use, all details are non-binding information and, as such, no guarantee of characteristics. This also applies to instructions from our technical advice service. Publication of this technical leaflet renders all previous ones invalid.
The contents of this datasheet may only be reproduced, copied or used for other purposes as extracts with the consent of Böker Sprühklebersysteme GmbH. Breaches will be prosecuted under criminal law.